



Scapa 3259

PVC Single Sided Foam Tape

DESCRIPTION

Scapa 3259 is primarily a foam compression sealant. The product is black. The foam is predominantly closed celled and is a medium hardness foam. An acrylic pressure sensitive adhesive is coated on one side, and the product has a paper release liner on the other non-adhesive face. Scapa 3259 will act as a water-seal and air/dust seal when compressed.

APPLICATIONS

- For anti slip mounting
- For gap filling
- For cushioning
- For preventing electrolytic corrosion

PRODUCT BENEFITS

- Clean to use / clean edge finish
- Pre-determined dimensional sealant reduces waste
- No known hazards associated with this product
- Medium hardness multi-purpose foam seal, with similar properties to Neoprene
- Suitable for indoor and outdoor environments
- Resistance to abrasion, corrosion and moisture
- Very good Ultra violet {UV} Light resistant
- Paper release liner on the non-adhesive face, reducing dimensional change during application
- Good resistance to dilute acids & alkalis
- Coated on one side with a high quality pressure sensitive acrylic adhesive
- Shelf life of 1 year from dispatch
- Application temperature: +10oC to +40oC
- Service temperature: -30oC to +70oC
- Minimum 30% compression required to effect a water seal

Accreditation:

Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free).

Fire rated to DIN 4102 part 1, B2.

AbP DIN EN 13501-1:2010 Class E.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
Thermal Conductivity (k)	0.052	Wm ⁻¹ K ⁻¹	Lee's Disc
Tensile Strength	30	Ncm ⁻²	Scapa F17
Shore Hardness {00} Scale	35	"00"	Scapa F16
Force To Compress By 30 %	3.2	Ncm ⁻²	Scapa F4
Foam Density	130 (12 & 15mm 150)	Kg/m ³	Scapa F2
Elongation at Break	>155	%	Scapa F17
Compression Deflection After 1 Minute	2.7	Ncm ⁻²	Scapa F4
10 Minute 180° Peel Adhesion	5	N/25mm	Scapa F9

STANDARD PRESENTATIONS

- Thickness : 1.5; 3.0; 4.5; 6.0; 7.5; 9.0; 10.5; 12.0; 15.0 mm
- Formats: Logs, Rolls, Die Cuts, Spools
- Core: 76mm plastic

RECOMMENDATIONS

Surfaces must be clean, dry, free from grease and dirt. Recommended cleaning agent is Propan-2-ol, {IPA}. Please note manufacturer's safety instructions should be followed and customers are recommended to ensure compatibility of the solvent with their substrate. Ideal bonding substrates are those which are: clean, dry, flat, smooth, dust free & non-porous. Low temperatures may increase the risk of condensation, reducing the tack of the product. Life expectancy will vary with temperature and humidity. Product may be applied by hand direct from a roll applying even pressure. Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.